

BYCAST

TECHNICAL SPECIFICATIONS OF THE LEATHER

Type of leather:	split polyurethane refinishing
Origin:	European
Thickness:	1,3 – 1,5 mm
Average size:	3,0 – 3,5 sq. m
Tannage:	chrome salts
Dye:	penetrating
Finishing:	covered by film thickness less than 0,1 mm (without solvent)

TECHNICAL CHARACTERISTICS

Analysis	Test method	Unit of measurement	Recommended value
Color fastness to light	UNI EN ISO 105 B01		4-5
Color fastness to dry rubbing – color change - 250 cycles	UNI EN ISO 11640		5
Color fastness to dry rubbing –color staining 250 cycles	UNI EN ISO 11640		5
Color fastness to wet rubbing –color change - 250 cycles	UNI EN ISO 11640		5
Color fastness to wet rubbing –color staining 250 cycles	UNI EN ISO 11640		5
Reaction to repeat flexure	UNI EN ISO 5402		20 000 bending without defect

All submitted test results are obtained using official methods on non-manipulated leather. Eventual further tests made after using leather, must be agreed between producer and buyer.