

DAKOTA (Asportabile)

TECHNICAL SPECIFICATIONS OF THE LEATHER

Type of leather:	bovine
Origin:	European and non-European
Thickness:	0,9 – 1,1 mm
Average size:	4,0 – 4,3 sq. m
Tannage:	chrome salts
Dye:	aniline coloring
Finishing:	self-fixing resin
Appearance:	two-tone and rub-off effect

TECHNICAL CHARACTERISTICS

Analysis	Test method	Unit of measurement	Recommended value
Color fastness to dry rubbing – 500 cycles	UNI EN ISO 11640	Grey scale	4
Color fastness to wet rubbing – 80 cycles	UNI EN ISO 11640	Grey scale	4
Color fastness to alkaline sweat – 80 cycles	UNI EN ISO 11640	Grey scale	3/4
pH	UNI EN ISO 4045	–	3,2
Tear strength	EN ISO 3377-1	N	20
Dry flexing	UNI EN ISO 5402	–	20 000
Color fastness to light - xenotest	UNI EN ISO 105 B02	Bleu scale	5

All submitted test results are obtained using official methods on non-manipulated leather. Eventual further tests made after using leather, must be agreed between producer and buyer.